


Any Foam

INDIVIDUAL SPECIFICATION SHEET

Filter Foam 40ppi	
<u>GRADE/REF : 40ppi</u>	
<u>CHARACTERISTIC</u>	<u>SPECIFICATION</u>
APPARENT PIECE DENSITY	20-26 Kg/m ³
COMPRESSION LOAD DEFLECTION	4.1 kPa
TENSILE STRENGTH	90 Kpa (Min)
ELONGATION AT BREAK	125 % (Min)
CELL COUNT	1/CM MIN 10.0 MAX 13.0
SPECIFICATION	OPEN CELL POLYETHER BASED RETICULATED POLYURETHANE FOAM. WATER RESISTANT, HUMIDITY RESISTANT.

Physical properties are measured using test methods described in BS EN ISO 845:1995. (Determination of Density), BS EN ISO 2439 (Determination of Hardness) and BS EN ISO1798 (Determination of Tensile Strength and Elongation).



Any Foam

All prices include VAT
Next Day UK Delivery

Call us on Freephone
0800 193 4488

Anyfoam Ltd, 2 Falcon Way, Shire Park, Welwyn Garden City, Hertfordshire, AL7 1TW
www.anyfoam.co.uk