




Any Foam

INDIVIDUAL SPECIFICATION SHEET

Packaging (HLB) Foam		
<u>GRADE/REF : RP21250</u>		
<u>CHARACTERISTIC</u>	<u>SPECIFICATION</u>	<u>TEST METHOD</u>
APPARENT PIECE DENSITY	20–22 Kg/m ³	BS EN ISO 845 : 2009 (ISO 845 : 2006)
NOMINAL HARDNESS	225–275 Newtons	BS EN ISO 2439:METHOD B 2001
TENSILE STRENGTH	100 Kpa (Min)	BS EN ISO 1798: 2008
ELONGATION @ BREAK	100 % (Min)	BS EN ISO 1798: 2008
COMPRESSION SET (DRY)	15 % (Max)	BS EN ISO 1856: 2001
FORM ISSUE No. 4	RAISED: 18/03/09	ISSUED BY: L McQuillan



Any Foam

All prices include VAT
Next Day UK Delivery

Call us on Freephone
0800 193 4488

Anyfoam Ltd, 2 Falcon Way, Shire Park, Welwyn Garden City, Hertfordshire, AL7 1TW
www.anyfoam.co.uk