


# Any Foam

## INDIVIDUAL SPECIFICATION SHEET

<b>Memory Foam</b>	
<b><u>GRADE/REF : 50M</u></b>	
<b><u>CHARACTERISTIC</u></b>	<b><u>SPECIFICATION</u></b>
APPARENT PIECE DENSITY	48-52 Kg/m <sup>3</sup>
NOMINAL HARDNESS	70-100 Newtons
TENSILE STRENGTH	50 Kpa (Min)
ELONGATION @ BREAK	180 % (Min)
RESILIENCE	16% (Max)
RECOVERY RATE	5-20 Seconds
SPECIFICATION	Visco elastic, temperature sensitive foam for use in mattress applications.

MEETS WITH REQUIREMENTS OF SCHEDULE 1 PART 1 OF THE FURNITURE AND FURNISHINGS (FIRE) (SAFETY) AMENDED REGULATIONS 1989.

*Physical properties are measured using test methods described in BS EN ISO 845:1995. (Determination of Density), BS EN ISO 2439 (Determination of Hardness) and BS EN ISO1798 (Determination of Tensile Strength and Elongation).*



# Any Foam

All prices include VAT  
Next Day UK Delivery

Call us on Freephone  
**0800 193 4488**

Anyfoam Ltd, 2 Falcon Way, Shire Park, Welwyn Garden City, Hertfordshire, AL7 1TW  
[www.anyfoam.co.uk](http://www.anyfoam.co.uk)