


Any Foam

INDIVIDUAL SPECIFICATION SHEET

Memory Foam		
<u>GRADE/REF : 50M</u>		
<u>CHARACTERISTIC</u>	<u>SPECIFICATION</u>	
APPARENT PIECE DENSITY	48-52 Kg/m ³	
NOMINAL HARDNESS	70-100 Newtons	
TENSILE STRENGTH	50 Kpa (Min)	
ELONGATION @ BREAK	180 % (Min)	
RESILIENCE	16% (Max)	
RECOVERY RATE	5-20 Seconds	
SPECIFICATION	Visco elastic, temperature sensitive foam for use in mattress applications.	

MEETS WITH REQUIREMENTS OF SCHEDULE 1 PART 1 OF THE FURNITURE AND FURNISHINGS (FIRE) (SAFETY) AMENDED REGULATIONS 1989.

Physical properties are measured using test methods described in BS EN ISO 845:1995. (Determination of Density), BS EN ISO 2439 (Determination of Hardness) and BS EN ISO1798 (Determination of Tensile Strength and Elongation).



Any Foam

All prices include VAT
Next Day UK Delivery

Call us on Freephone
0800 193 4488